



THE LABORATORY  
AT THE BIRMINGHAM  
ASSAY OFFICE

P.O. BOX 151 NEWHALL STREET  
BIRMINGHAM B3 1SB ENGLAND  
TELEPHONE: +44 (0)121 236 6951  
FACSIMILE: +44 (0)121 236 3228

www.theassayoffice.co.uk  
testing@theassayoffice.co.uk

Ian West  
Ecos Organic Paints  
Unit 19, Heysham Business Park  
Middleton Road  
Heysham  
Lancashire  
LA3 3PP

Test Report

Ref: 89398	Date work reported: 19 October 2012
Page: 1 of 2	Date work received: 16 October 2012

Method:	The procedures described in BS EN 71-3: 1995 incorporating Amendment No. 1 and Corrigendum No. 1, EN 71-3: 1994 inc. Amendment A1 – Specification for migration of certain metals
---------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Sample Description:

Sr No.	Test	Results
1	Paint Samples	PASS

Measurement of migration of certain elements by ICP-OES analysis

Clause	Test
8.1	Coating of paints, varnish and similar coatings
8.2	Polymeric and similar materials, whether textile reinforced or not, but excluding other textile
8.3	Paper and paper board
8.4	Textile, whether natural or synthetic
8.5	Glass/Ceramic/Metallic Material
8.6	Other materials whether mass coloured or not
8.7	Material intended to leave trace
8.8	Pliable modelling materials, including modelling clays and gels
8.9	Paints, including finger paints and similar materials in solid or liquid form appearing as such in the toys

- All samples were adjusted to 1mol/l if kept for more than the working day.

Note: The information contained in this report is given in good faith on the basis of samples and information received. The Assay Office does not take responsibility for the Customer's interpretation of the report nor any consequence arising from this. This test report shall not be reproduced except in full, without written approval of the Assay Office. Our standard conditions and tolerances apply. Opinions and interpretations are outside the scope of accreditation.



Ref: 89398	Date work reported: 19 October 2012
Page: 2 of 2	Date work received: 16 October 2012

**Materials Sampled (and sample weight if less than 100mg)**


Sample No.	Description	Weight (mg)
<b>Paint Samples</b>		
1	KDS Yellow Paint (Clause 8.1)	
2	Violet Paint (Clause 8.1)	
3	Magenta Paint (Clause 8.1)	
4	Carmines Paint (Clause 8.1)	


**Results:**

Element	Results (mg/kg) Corrected in accordance with clause 4.2				Limits mg/kg	Method
	1	2	3	4		
Arsenic	<10	<10	<10	<10	25	ICP Technique
Mercury	<10	<10	<10	<10	60	ICP Technique
Selenium	<10	<10	<10	<10	500	ICP Technique
Barium	<20	<20	<20	<20	1000	ICP Technique
Lead	<10	<10	<10	<10	90	ICP Technique
Antimony	<10	<10	<10	<10	60	ICP Technique
Chromium	<10	<10	<10	<10	60	ICP Technique
Cadmium	<10	<10	<10	<10	75	ICP Technique

Remarks: Sample weight of items marked with a ~ were less than 100mg. The toxic metal content has been calculated as though the sample weight were 100mg in accordance with Clause 8.1.1.

**Conclusion:** The results of the test carried out MEET the requirements of the requested standard.

  
H. Singh BSc, C.CHEM, MRSC  
Senior Analytical Chemist (Inorganic)

  
S. Deverell BSc  
Assistant Analytical Chemist

LG 11.09

*Note: The information contained in this report is given in good faith on the basis of samples and information received. The Assay Office does not take responsibility for the Customer's interpretation of the report nor any consequence arising from this. This test report shall not be reproduced except in full, without written approval of the Assay Office. Our standard conditions and tolerances apply. Opinions and interpretations are outside the scope of accreditation.*